

## HP COLOUR LASER



Substance g/m <sup>2</sup>	90	100	120	160	200
Caliper $\mu$ m (approx)	100	110	129	173	217
Opacity (ISO) %	93	95	97	98	
Brightness (ISO) D65	110	110	110	110	110
Whiteness CIE D65	160	160	160	160	160
Smoothness (Bendtsen) ml/min TS	60	60	60	60	60
Smoothness (Bendtsen) ml/min WS	60	60	60	60	60
Rigidity (Taber Stiffness Units) 15° MD	2.7	3.6	4.9	15.5	29
Rigidity (Taber Stiffness Units) 15° CD	1.7	1.9	2.9	9.3	16
Surface pH	8.4	8.4	8.4	8.4	8.4

## Technical Capability

Copier Guaranteed	Yes
Laser Guaranteed	Yes, mono and colour
Permanence of Paper	Yes, meets ISO9706 requirements for Permanence of Paper

## Environmental Information

Fibre Source	Virgin wood fibre from France
Bleaching	Pulp is bleached using an Elemental Chlorine Free (ECF) process
Disposal	This material can be disposed of by recycling or incineration for energy recovery
Accreditation	Produced at a mill that is certified to the ISO14001 environmental management standard

The Robert Horne Group is committed to the responsible purchasing of paper products. This commitment will be realised through a stepwise approach to responsible purchasing that utilises the best available techniques and information. Robert Horne requires its suppliers to abide by all local, state and national laws and international conventions. For further information and full Responsible Paper Purchasing Policy, visit: <http://www.roberthorne.co.uk/environment>